

Stainless Steel - 1.4301 (304) Sheet and Coil

SPECIFICATIONS

Commercial	304
------------	-----

Stainless steel types 1.4301 and 1.4307 are also known as grades 304 and 304L respectively. Type 304 is the most versatile and widely used stainless steel. It is still sometimes referred to by its old name 18/8 which is derived from the nominal composition of type 304 being 18% chromium and 8% nickel.

Type 304 stainless steel is an austenitic grade that can be severely deep drawn. This property has resulted in 304 being the dominant grade used in applications like sinks and saucepans.

Type 304L is the low carbon version of 304. It is used in heavy gauge components for improved weldability. Some products such as plate and pipe may be available as "dual certified" material that meets the criteria for both 304 and 304L.

304H, a high carbon content variant, is also available for use at high temperatures.

Property data given in this document is typical for flat rolled products covered by EN 10088-2:2005. ASTM, EN or other standards may cover products sold. It is reasonable to expect specifications in these standards to be similar but not necessarily identical to those given in this datasheet.

CHEMICAL COMPOSITION

EN 10088-2:2005 1.4301 steel	
Element	% Present
Chromium (Cr)	17.50 - 19.50
Nickel (Ni)	8.00 - 10.50
Manganese (Mn)	0.0 - 2.00
Silicon (Si)	0.0 - 1.00
Nitrogen (N)	0.0 - 0.11
Carbon (C)	0.0 - 0.07
Phosphorous (P)	0.0 - 0.05
Sulphur (S)	0.0 - 0.02
Iron (Fe)	Balance

ALLOY DESIGNATIONS

Stainless steel grade 1.4301/304 also corresponds to the following standard designations **but may not be a direct equivalent:**

S30400
304S15
304S16
304S31
EN58E

SUPPLIED FORMS

- Sheet
- Strip

GENERIC PHYSICAL PROPERTIES

Property	Value
Density	8.00 g/cm ³
Melting Point	1450°C
Thermal Expansion	17.2 x10 ⁻⁶ /K
Modulus of Elasticity	193 GPa
Thermal Conductivity	16.2 W/m.K
Electrical Resistivity	0.72 x10 ⁻⁶ Ω .m

MECHANICAL PROPERTIES

EN 10088-2:2005 sheet up to 8mm thick	
Property	Value
Proof Stress	230 Min MPa
Tensile Strength	540 - 750 MPa
Elongation A50 mm	45 Min %

Properties above are for 1.4301 sheet/plate

DISCLAIMER This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon. Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date. The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources. Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards. As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied. Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.



Stainless Steel - 1.4301 (304) Sheet and Coil

Last Updated 13 March 2020

EN 10088-2:2005 plate from 8mm to 75mm thick	
Property	Value
Proof Stress	210 Min MPa
Tensile Strength	520 - 720 MPa
Elongation A50 mm	45 Min %

Properties above are for 1.4301 sheet/plate

APPLICATIONS

304 stainless steel is typically used in:

- Sinks and splashbacks
- Saucepans
- Cutlery and flatware
- Architectural panelling
- Sanitaryware and troughs
- Tubing
- Brewery, dairy, food and pharmaceutical production equipment
- Springs, nuts, bolts and screws

CORROSION RESISTANCE

304 has excellent corrosion resistance in many environments and when in contact with different corrosive media. Pitting and crevice corrosion can occur in environments containing chlorides. Stress corrosion cracking can occur above 60°C.

HEAT RESISTANCE

304 has good resistance to oxidation in intermittent service up to 870°C and in continuous service to 925°C. However, continuous use at 425-860°C is not recommended if corrosion resistance in water is required. In this instance 304L is recommended due to its resistance to carbide precipitation.

Where high strength is required at temperatures above 500°C and up to 800°C, grade 304H is recommended. This material will retain aqueous corrosion resistance

FABRICATION

Fabrication of all stainless steels should be done only with tools dedicated to stainless steel materials. Tooling and work surfaces must be thoroughly cleaned before use. These precautions are necessary to avoid cross contamination of stainless steel by easily corroded metals that may discolour the surface of the fabricated product.

COLD WORKING

304 stainless steel readily work hardens. Fabrication methods involving cold working may require an intermediate annealing stage to alleviate work hardening and avoid tearing or cracking. At the completion of fabrication a full annealing operation should be employed to reduce internal stresses and optimise corrosion resistance.

HOT WORKING

Fabrication methods, like forging, that involve hot working should occur after uniform heating to 1149-1260°C. The fabricated components should then be rapidly cooled to ensure maximum corrosion resistance.

MACHINABILITY

304 has good machinability. Machining can be enhanced by using the following rules:
Cutting edges must be kept sharp. Dull edges cause excess work hardening.

Cuts should be light but deep enough to prevent work hardening by riding on the surface of the material.

Chip breakers should be employed to assist in ensuring swarf remains clear of the work.

Low thermal conductivity of austenitic alloys results in heat concentrating at the cutting edges. This means coolants and lubricants are necessary and must be used in large quantities.

HEAT TREATMENT

304 stainless steel cannot be hardened by heat treatment.

Solution treatment or annealing can be done by rapid cooling after heating to 1010-1120°C.

WELDABILITY

Fusion welding performance for type 304 stainless steel is excellent both with and without fillers. Recommended filler rods and electrodes for stainless steel 304 is grade 308 stainless steel. For 304L the recommended filler is 308L. Heavy welded sections may require post-weld annealing. This step is not required for 304L. Grade 321 may be used if post-weld heat treatment is not possible.

DISCLAIMER This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon. Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date. The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources. Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards. As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied. Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.

