

Stainless Steel - 1.4512 Sheet and Coil

Last Updated 13 March 2020

SPECIFICATIONS

Commercial	409
EN	1.4512

Grade 409 / 1.4512 titanium stabilised ferritic stainless steel is often referred to as 'muffler grade stainless steel' since the major bulk usage of this material is for automotive exhaust systems.

CHEMICAL COMPOSITION

EN 10088-2:2005 1.4512 Steel	
Element	% Present
Chromium (Cr)	10.50 - 12.50
Silicon (Si)	0.0 - 1.00
Manganese (Mn)	0.0 - 1.00
Titanium (T)	0.0 - 0.65
Carbon (C)	0.0 - 0.30
Phosphorous (P)	0.0 - 0.04
Sulphur (S)	0.0 - 0.02
Iron (Fe)	Balance

SUPPLIED FORMS

Grade 409 / 1.4512 is a rolled product (sheet, coil and strip) material usually available up to a maximum of 2.5mm thickness.

Grade 1.4003 is similar though not a direct equivalent but is available in thicker sheets and plates.

- Sheet

GENERIC PHYSICAL PROPERTIES

Property	Value
Density	7.60 g/cm ³
Modulus of Elasticity	208 GPa
Thermal Conductivity	25.8 W/m.K
Electrical Resistivity	0.60 x10 ⁻⁶ Ω .m

MECHANICAL PROPERTIES

EN 10088-2:2005 sheet up to 8mm thick	
Property	Value
Proof Stress	210 Min MPa
Tensile Strength	380 - 560 MPa
Elongation A50 mm	25 Min %

WELDABILITY

Weldability of grade 409 is good up to about 2.5mm thick.

If welding of thicker material is necessary, then grade 1.4003 should be selected.

DISCLAIMER This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon. Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date. The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources. Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards. As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied. Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.

